

# ALUMINUM PIPE — SCHEDULE 40

6061-T6 6063-T6

I.P.S. in Inches	Diameter Inches		Wall Thickness Inches	Weight per Foot
	Outside	Inside		
⅜	.405	.269	.068	.085
¼	.540	.364	.088	.147
⅝	.675	.493	.091	.196
½	.840	.622	.109	.294
¾	1.050	.824	.113	.391
1	1.315	1.049	.133	.581
1¼	1.660	1.380	.140	.786
1½	1.900	1.610	.145	.940
2	2.375	2.067	.154	1.260
2½	2.875	2.469	.203	2.000
3	3.500	3.068	.216	2.620
3½	4.000	3.548	.226	3.150
4	4.500	4.026	.237	3.730
5	5.563	5.047	.258	5.060
6	6.625	6.065	.280	6.560
8	8.625	7.981	.322	9.880
10	10.750	10.020	.365	14.000
12	12.750	12.000	.375	17.140

# ALUMINUM PIPE — SCHEDULE 80

6061-T6

I.P.S. in Inches	Diameter Inches		Wall Thickness Inches	Weight per Foot
	Outside	Inside		
1	1.315	.957	.179	.75
1¼	1.660	1.378	.191	1.04
1½	1.900	1.500	.200	1.25
2	2.375	1.939	.218	1.74
3	3.500	2.900	.300	3.54
3½	4.000	3.364	.318	4.33
4	4.500	3.826	.337	5.18
5	5.563	4.813	.375	7.26
6	6.625	5.761	.432	9.98
8	8.625	7.625	.500	15.16